

1. Product


 **Everlux**[®] Photoluminescent marking rolls, anti-slip, for floor application.

2. Product Description

Self-adhesive photoluminescent vinyl rolls with 0.39mm, with a layer of monomeric calendared transparent rigid plastic with 0.17mm, with anti-slip characteristics:



Representation of the roll layers:



- 1 – Anti-slip layer
- 2 – Photoluminescent vinyl
- 3 – Adhesive

3. Abrasion and Slip-Resistance

Self-adhesive photoluminescent vinyl rolls are resistant to slipping. The slip resistance is characterized by the coefficient of static and dynamic wet friction, through ANSI A 137.1: 2012 and ANSI B 101.1: 2009:

Dynamic coefficient of friction (ANSI A 137.1:2012)	
Wet	0.236
Static coefficient of friction (ANSI B 101.1:2009)	
Wet	0.452

4. Photoluminescent proprieties

The Everlux adhesive vinyl products are fully conform to the International standards NS 3926-2, DIN 67510-1, ISO 16069, and IMO A.752 (18) Resolution When stimulated with 1000lux during 5 minutes, the photoluminescent characteristics are as follows:

Photoluminescent anti-slip Everlux Vinyl

Time after removing the exciting light (in minutes)	Luminescent intensity (mcd/m ²)
10 minutes	215
60 minutes	30
Luminescent intensity 100 times greater than the limit of human visibility	Period of light decay (minutes)
0.30 mcd/m ²	3100

5. Dimensions, Pictograms and Colours

The products are according with the Everlux catalogue and are according to National and International Norms and Legislation.

6. Positioning and Mounting

The installation of the product must follow the following indications:

Preparation of the application surface:

All surfaces on which signs are to be installed shall be considered as contaminated.

Cleaning and Degreasing - For this operation a degreasing solution must be used; for example, isopropyl alcohol in the proportion 70% isopropyl alcohol and 30% water.

The cleaning operation must be done in two phases:

- Start by applying the degreasing solution to the surface and clean the whole surface in circular movements with a paper or cloth that does not leave residues, to remove dirt and grease;
- Proceed by applying a second dosage of the degreasing solution to the surface and, this time, cleaning it with movements in only one direction.

Drying – Let it dry, waiting 2 to 3 minutes until all cleaning solution evaporates. Do not touch the previously cleaned and degreased surfaces with your fingers.

Primary application – Apply a thin, uniform coating to the bonding surface. Use the minimum amount that will fully coat the area to be taped.

Application may be done with a clean lint-free cloth, pad, felt tipped dauber, absorbent paper towel or disposable tissue. Brushes, rollers, or spraying tend to apply excessive amounts should therefore be avoided.

Allow to dry completely prior to application of adhesive safety sign. Depending on temperature and humidity, the drying and reacting time of adhesion promoter can vary. Typical drying time will be 1-2 minutes.

Apply the adhesive safety sign within 8 hours or reapply adhesion promoter.

We suggest the usage of 3M™ Adhesion Promoter 111.

Product application

Removal of the protective paper from the sign adhesive - Remove the adhesive backing paper in one corner of the product without touching the adhesive.

Application of the product - Apply the sign in the previously prepared place, avoiding the formation of bubbles and exerting pressure throughout the sign area. It is recommended to use a roller for better distribution of forces throughout the surface.

Photoluminescent anti-slip Everlux Vinyl

The quality of the adhesion will depend on the amount of contact between the adhesive and the installation surface. A strong, homogenous pressure promotes union.

The application should be made at the room temperature between 15°C and 25°C, and never be less than 15°C.

Once applied, at the recommended application temperature, possible temperature changes are generally well tolerated by the glue, without modifying the adhesion properties of the glue.

Adhesion time - Until adhesion is considered complete, some time is required: approximately 50% final adhesion is obtained after 20 minutes, 90% after 24 hours and 100% after 72 hours (at room temperature).

Caution - before installation it is essential that the installer evaluate the surface where the signs are to be installed:

Rough or porous surfaces - A rough or porous surface will not allow the application of self-adhesive elements and may require other installation type.

Parallelism of the surface to be installed - Surface parallelism is essential to adhesion quality. On surfaces where there is no complete parallelism, the need for alternative installation solutions such as mastic glue or structural glue, or bolting to support structures or directly to the surface, must be considered.

Curved Surfaces - Self-adhesive products are ideal for flat surfaces. Although the application on curved surfaces is possible, it must be verified in each case whether the tension created by the curvature of the surface does not exceed the adhesiveness of the product.

Special surfaces - Some surfaces have special characteristics such as the presence of coatings that impart specific characteristics to the surfaces. This type of surface usually has a low surface energy and may require special preparation. It is the responsibility of the installer to evaluate the surface and, if necessary, to ask the manufacturer for instructions on the correct preparation of the surface.

For further information please consult the Everlux Installation Guide for self-adhesive products:



7. Maintenance

The Everlux safety signs shall be visually inspected and cleaned at appropriate intervals by a competent person. Any deterioration, discoloration or missing component shall be recorded for immediate replacement. The illuminating sources shall be checked as to whether the sources are working or not. Any missing or failed lamp and luminaire shall be noted for repair or replacement.

The surface and edges of Everlux products shall be cleaned using a wet cloth at appropriate intervals by a competent person.

8. Guarantee

Under suitable conditions of application and in indoor environment and proper cleaning, a guarantee of 3 years is provided against defects of manufacture.

Exposure to the following conditions may affect the durability of the product:

- Submersion or jets of water, as well as humid environments and leaks may reduce the strength of the product and as such the warranty period.
- For outdoor applications, considering the possibility of exposure to temperature and other extreme environments, this period may be shortened.

For a longer product life, consideration should be given to the type and state of the application surface, the type of movement to be subjected and the methods of cleaning. Refer to point 6 of this data sheet.

9. Health and safety

The product does not contain any radioactive substances. In toxic terms the product is considered as safe (European norm EN 71-3).

10. Quality

The quality of Everlux products is ensured by a rigorous process of quality control with tests in our own laboratory observing all applicable norms.

11. Legislation and Normative references

The products are in conformity to the following norms:

- ISO 16069
- EN ISO 7010
- ISO 3864, part 1,2, 3 and 4
- ISO 15370
- NFPA 101 – Life Safety Code
- European directive 92/58/CEE
- BS 5499-4
- Norms ISO 3864
- Norms DIN 67510
- UAE Fire and Life Safety Code of Practice
- Saudi Building Code Fire Protection Requirements (SBC 801)